



BioRoot™ RCS a new biomaterial for root canal filling

Anne Charlotte FLOURIOT
Stéphane SIMON



Introduction

Due to progresses in scientific knowledge, endodontic treatments provide now highly predictable results. However, such results are closely tied to the respect of a number of steps that are nowadays clearly identified as key elements for endodontic treatment success. Notably, the filling of the root canal is one of them. In clinical application, it requires both knowledge and thoroughness (Ray and Trope, 1995).

Sterilizing and obtaining a root canal free of bacteria, following disinfection, is, so far, impossible to obtain (Siqueira et al 1997). A part from disinfecting, the obturation act is responsible to trap residual bacteria, fill the pre-disinfected space and ultimately seal it, in order to avoid any bacterial leakage into the periapical area.

Modern techniques for filling the root canal are based on the association of gutta percha (the core of the filling) and a sealer. The latter acts as a sealing material and, because of its fluidity, it is able to spread into any free space, notably those which were not enlarged during the mechanical root canal preparation.

Depending on the technique used by the practitioner, the gutta percha is compacted differently: laterally when used with cold lateral condensation

or vertically when used with a warm vertical compaction. Both techniques provide good long term results, as the root canal is filled with a high proportion of gutta percha with a small volume of sealer. The quantity of the latter needs to be minimal, as being degradable, it may lead to a canal bacterial contamination in the time.

The single cone technique, a procedure introduced in the past, is still very popular among practitioners being quick and easy to perform. This technique consists in by employing a single cone with a large amount of sealer, which acts as a filling material. Unfortunately, the currently used sealers are poorly resistant to dissolution. As a consequence, with time, the canal is again contaminated with bacteria, leading to treatment failure and the growth of an apical lesion. Thereby, although being easy to accomplish, the single cone technique is not recommended for root canal filling (Beatty 1987; Pommel et Camps 2001).

However, the single technique may be re-opened and provided new reliability with new proposed biomaterials based on bioceramics, developed in the last decades and launched on the market as root canal sealers.

Bioceramics properties

Bioceramics are specifically designed for medical and dental use with the prefix 'bio' referring to their biocompatibility. In the orthopedic field, inert bioceramics are used for prosthetic devices, while the active and re-absorbable ones are applied in the endodontic field.

They are composed of alumina, zirconia, bioactive glass, glass ceramics, coatings, composites, hydroxyapatite, resorbable calcium phosphates and radiotherapy glasses (Dubock 2000; Best et al 2008). Among them, calcium phosphate-based materials are used for filling bone defects.

Calcium silicates and bio-aggregates (Mineral Trioxide Aggregate for example) were introduced for apical plug in apexification procedures but also for coronal/root repair in case of perforations (Trope and Debelian 2014, Koch and Brave 2009). Three basic types of bioceramics must be distinguished: (1) bio-inert high strength ceramics (alumina, zirconia and carbon), (2) bioactive ceramics which form direct chemical bonds with the bones or soft tissues of a living organism (Bioglass and glass ceramics) and (3) biodegradable/soluble/re-absorbable ceramics

(calcium phosphate based ceramics) that actively participate in the metabolic processes of an organism.

According to the manufacturers, such sealers could be used alone or combined with a gutta percha point using a single cone technique in the context of an endodontic treatment or retreatment (Koch and Brave 2009 part 3). These sealers are mainly composed of tricalcic silicate, calcium phosphate monobasic, calcium hydroxide, and zirconium oxide that closely resemble the composition of MTA (Tyagi et al., 2013). The premixed form facilitates their use in good conditions, with decreased risk of heterogeneity in the preparation (Yang and Lu, 2008).

Bioceramics have shown remarkable properties in terms of biocompatibility and antimicrobial activity with an excellent bioactivity, capable to induce mineralization of periapical tissues (Zhang et al., 2009; Zhang et al., 2010). Indeed, the bioceramics specific physico-chemical properties are what make them so interesting for the endodontic field. Firstly, because of their hydrophilic profile, they can set in a humid environment, such as dentin, which is made of nearly 20% of water (Koch and Brave, 2010, part 2). Secondly, due to their wettability, a decreased viscosity and a higher quality sealing is present in bioceramics when compared with all the currently marketed sealers.

Specific properties and composition

BioRoot™ RCS is the newest endodontic sealer based on tricalcic silicate materials benefiting from both Active Biosilicate Technology and Biodentine™.

The first provides medical grade level of purity and, unlike “Portland cement” based materials, it ensures the purity of the calcium silicate content with the absence of any aluminate and calcium sulfate. BioRoot™ RCS is a mineral based root canal sealer using tricalcium silicate setting system. The powder part additionally contains zirconium oxide as biocompatible radiopacifier and a hydrophilic biocompatible polymer for adhesion enhancing. The liquid part contains mainly water, calcium chloride as a setting modifier and a water reducing agent.

BioRoot™ RCS is bioactive by stimulating bone physiological process and mineralization of the dentinal structure (Camps 2015, Dimitrova-Nakov 2015,). Therefore it creates a favorable environment for periapical healing and bioactive properties including biocompatibility (Reichl 2015), hydroxyapatite formation, mineralization of dentinal structure, alkaline pH and sealing properties.

BioRoot™ RCS is indicated for the permanent root canal filling in combination with gutta-percha

points and is suitable for use in single cone technique or cold lateral condensation (Camilleri, 2015). BioRoot™ RCS was designed to be used by mixing powder part with the liquid part by simple spatulation: there is no need of a mixing machine. The working time is around 15 minutes and the setting time is less than 4 hours in the root canal. In addition, BioRoot™ RCS displayed a tight seal with the dentin and the gutta-percha (Xuereb 2014) and an appropriate radiopacity. The paste is of smooth consistency with good flow and adequate adhesion to instruments in order to enable an optimal placement in the root canal.

Thanks to the use of Active BioSilicate Technology which is monomer free, there is no shrinkage of BioRoot™ RCS during setting for reaching a tight seal of the root canal.

Despite the similar composition in terms viscosity and texture with a sealer, BioRoot™ RCS must be considered as an adhesive root filling material. A fitted gutta-percha point is used as a plugger-like carrier to facilitate the flow of BioRoot™ RCS into the canal space. Indeed, BioRoot™ RCS is also recommended for facilitating the obturation removal in case of retreatment.

A new concept of obturation

To achieve root canal filling and prevent any bacterial or fluid leakage, practitioners were always told to associate a core material with a sealer in order to fill the canal space. So far, gutta-percha is the most used material because it is a non-resorbable and well bio-tolerated. Unfortunately, gutta-percha has no intrinsic adhesive properties to dentin. Thereby, in order to ensure the seal of the final filling, the use of a sealer is required. The latter is also used for filling voids, flowing into anatomical irregularities, notably the ones which were not enlarged by the mechanical preparation (i.e. isthmus, lateral/accessory canals).

Nevertheless, sealers are subjected to shrinkage, overtime degradation and have no chemical sealing ability to dentin. As a consequence, the use of a large amount of core material with the thinnest layer of sealer is recommended to improve the quality of the filling.

Among the obturation techniques, cold lateral and warm vertical compaction are the best ones. Indeed, they are both capable of pushing the sealer into the non-instrumented spaces, where residual bacteria may persist. However, the first technique leaves excessive cold sealer inside the canal irregularities (instead of leaving gutta percha) and the second one requires the placement of a plugger within 4 mm of the apex. Furthermore, with the warm lateral compaction, a large volume of coronal dentin need to be removed causing concerns among practitioners as it may possibly weaken the tooth structure (Trope and Debelian 2014).

Moreover, these techniques are time consuming, highly operator-dependent and require the use of visual aids to ensure the best chances of success. As a matter of fact, most of the general practitioners still use the single cone technique, as it is easy and quick to perform. Due to the introduction of Nickel Titanium tapered instrumentation, gutta-percha cones fitting in taper and apical diameter with the last file used of a given system are now commercialized. The

apical sealing ability of a single cone placed inside the root canal is achieved in such condition in the apical third, because of the concordance of the last file used and the gutta cone design. However, because of the non-circular shape of the canal section on the median and coronal thirds, the cone does not perfectly fit into an ovoid canal. Hence, the remaining space is filled with sealer or voids (Angerame et al., 2012; Schäfer et al., 2013; Somma et al., 2011). On this basis, the single cone technique cannot be considered as reliable since it provides an imperfect sealing.

Bioceramic sealers may be considered as an interesting solution to make the obturation steps reliable and easier to achieve, potentially replacing the ZnO-eugenol based sealers. In this context, they might provide a 3D tight and durable sealing all along the entire length of the root canal without the need of any compaction procedure. Used in combination with an adjusted gutta-percha point and due to its excellent wettability and viscosity, the bioceramic could spread into any root canal irregularity and non-instrumented space. Furthermore, its adhesive properties to dentin and the reduced need of an excessive coronal tissue removal would provide an improved resistance to root fracture in time. This new class of materials could finally simplify the obturation stage, making it reproducible in every practitioner's hands with a reduced learning curve. Above all, such technique could provide equivalent clinical results, if not even better, when compared to the gold standards. Notably among them, BioRoot™ RCS is one of these new bioceramic materials. The purpose of the present article is to describe its properties and introduce a new way of considering this biomaterial, not as a sealer but as a true root canal filling material. If this material can be considered as reliable, we may assist to a true paradigm shift into the field of endodontics.

Description of the technique and case report

From an operational point of view, the procedure is very similar to the single cone technique. However, few indispensable differences justify the reliability of BioRoot™ RCS with such technique. Notably, the single cone technique seals a cone alone. Instead, here the cone is employed as a carrier, which is left in place to allow the material removal in case of retreatment. Indeed, it must not be considered as the core of the filling. The obturation is made by BioRoot™ RCS itself.

Case report :

A pulp necrosis was diagnosed on tooth #36 of a 47 years old male patient. (Fig. 1)

- After having shaped the root canal and obtained an appropriate tapered preparation, the canal was disinfected with a 3% sodium hypochlorite solution activated with mechanical agitation. A final rinse with 17% EDTA and a final flush with sodium hypochlorite were completed before fitting the gutta percha cones.
- Canals were dried with paper points.
- BioRoot™ RCS was mixed, following manufacturer recommendations.
- Each gutta percha point was poured into the mixed material to largely cover the surface of the cone. Afterward, it was gently inserted into the root canal space until reaching the working length.
- The cone was cut at the entrance of the root

canal with a heat carrier, and a slight plug was created with a hand plugger.

- The second and the third canal were filled in the same way (Fig. 2).
- The patient was referred to the general practitioner who restored the tooth with a post and core, and a crown.
- Patient was recalled at 6, 12 and 24 months after treatment. *NB: the patient was treated in the frame of a randomized clinical trial (see below), explaining why he was recalled three times (Fig. 3).*

On the 24 months follow up radiograph, there were no signs of bone inflammation. This event is associated with no claims of pain nor discomfort by the patient and that the tooth was functional. Thereby, the treatment maybe considered as successful.

This case report is one of the 22 clinical cases of a randomized clinical trial comparing the succes of an endodontic treatment using warm vertical compaction of Gutta percha versus the above described BioRoot™ RCS. Currently, as the 24 months follow up period is still ongoing, some of the clinical cases are still not complete. The RCT registration number is NCT01728532 and the full protocol is available on <https://clinicaltrials.gov>

The results are still under analysis and very encouraging, which it allows us to consider this technique as reliable enough to be described here.



Fig. 1: Pre-operative X ray of tooth #36 on a 47 years old man.




Fig. 2: Post-operative X ray after completion of endodontic treatment. Canals were shaped with WaveOne Gold (Dentsply-France), disinfected with 3% sodium hypochlorite solution and the filled with BioRoot™ RCS placement with the help of 6% taper gutta percha cone.




Fig. 3: 24 months post-operative recall.

Conclusion

Endodontics is continuously under evolution. In the last 20 years, instrumentation research and development have been very active. Currently, disinfection and irrigation procedures are the two most focused aspects of endodontic research.

The shaping procedures and root canal disinfection have considerably been simplified. Thereby, every practitioner interested in endodontics is now able to complete any easy/middle difficulty root canal treatment with reproducible results without

any issue. Obturation, the final step of the procedure, is usually the most difficult and time consuming operation. However, with this new approach of root canal filling, this milestone may be overpassed. Considering the fluidity of BioRoot™ RCS as a filler and not only as a sealer, this represents a true paradigm shift. The preliminary results of the randomized clinical trial are very encouraging. More clinical investigations will be necessary in the future to confirm this new vision of a simpler root canal obturation.



Authors:

Stéphane Simon, DDS, MPhil, PhD, DSc

Senior Lecturer in Oral Biology and Endodontics – University of Paris Diderot (Paris 7), France

Associate Researcher (University of Birmingham, UK)

Dr. Simon is a full time academic with a practice limited to Endodontics. He is the Director of the Endodontic Program at Paris-Diderot University (France). His research topics are Pulp Biology, physiology and pathology, Tissue engineering and regenerative Endodontics.



Anne-Charlotte Flouriot, DDS

Dr Flouriot obtained the European Endodontology Diploma after she graduated as a DDS. She works in a private practice in the center of Paris.

References

- Angerame D, De Biasi M, Pecci R, Bedini R, Tommasin E, Marigo L, Somma F. Analysis of single point and continuous wave of condensation root filling techniques by micro-computed tomography. *Ann Ist Super Sanita*. 2012;48(1):35-41.
- Best SM, Porter AE, Thian ES, Huang J. Bioceramics: Past, present and for the future, *Journal of the European Ceramic Society* 2008; 28:1319–1327
- Beatty RG. The effect of standard or serial preparation on single cone obturation. *Int Endod J* 1987;20:276 - 81
- Camps et al. Bioactivity of a calcium silicate-based endodontic cement (BioRoot™ RCS): interactions with human periodontal ligament cells in vitro, *J Endod* 2015 Sept; 41 (9): 1469–73
- Dimitrova-Nakov et al., Bioactivity of BioRoot™ RCS, a root canal sealer, via A4 mouse pulpal stem cells in vitro. *2015 Dental Materials* : available online.
- Dubok VA. Bioceramics yesterday, today, tomorrow. *Powder Metallurgy and Metal Ceramics* 2000; 39(7-8)
- Koch K, Brave D. Bioceramic technology — the game changer in endodontics. *Endodontic Practice US*.2009;12:7–11
- Koch KA, Brave GD, Nasseh AA. Bioceramic technology: closing the endo-restorative circle, part 2. *Dentistry today*. 2010; 29(3):98-100
- Koch KA, Brave D. Endosequence: melding endodontics with restorative dentistry, part 3. *Dent Today*. 2009, 28(3):88-90
- Pommel L, Camps J. In vitro apical leakage of system B compared with other filling techniques. *J Endod*. 2001 Jul;27(7):449-51.
- Ray HA, Trope M. Periapical status of endodontically treated teeth in relation to the technical quality of the root filling and the coronal restoration. *Int Endod J*. 1995 Jan;28(1):12-8.
- Reichl FX1,2, Rothmund L1,2, Shehata M1,2, Högg C1,2 DNA double-strand breaks caused by new and contemporary endodontic sealers. *Int Endod J*. 2015 Nov 17.
- Schäfer E1, Köster M, Bürklein S. Percentage of gutta-percha-filled areas in canals instrumented with nickel-titanium systems and obturated with matching single cones. *J Endod*. 2013 Jul;39(7):924-8.
- Siqueira JF, Arujo MCP, Garcia PF, Fraga RC, Saboia Dantas CJ. Histologic evaluation of the effectiveness of five instrumentation techniques for cleaning at the apical third of root canals. *J Endod* 1997; 23:499-502.
- Somma F1, Cretella G, Carotenuto M, Pecci R, Bedini R, De Biasi M, Angerame D. Quality of thermoplasticized and single point root fillings assessed by micro-computed tomography. *Int Endod J*. 2011 Apr;44(4):362-9.
- Trope M, Debelian G. Bioceramic Technology in Endodontics. *Inside dentistry*. 2014 nov: 53-57
- Tyagi S, Mishra P, Tyagi P. Evolution of root canal sealers: An insight story. *European journal of dentistry*. 2013; 2(3):199
- Xuereb et al., 2014 In Situ Assessment of the Setting of Tricalcium Silicate-based Sealers Using a Dentin Pressure Model, *J Endod*. 2015 Jan;41(1):111-24.
- Yang Q, Lu D. Premixed biological hydraulic cement paste composition and using the same. Patent application 2008029909, December 4, 2008.
- Zhang H, Shen Y, Ruse ND, Haapasalo M. Antibacterial activity of endodontic sealers by modified direct contact test against *Enterococcus Faecalis*. *Journal of endodontics* 2009;35(7):1051-5
- Zhang W, Li Z, Peng B. Effects of iRoot SP on mineralization-related genes expression in MG63 cells. *Journal of endodontics*. 2010; 36(12):1978-82
- Zhang W, Li Z, Peng B. Ex vivo cytotoxicity of a new calcium silicate based canal filling material. *International endodontic journal*. 2010;42(9):769-74

OBTURATION
INNOVATION

BioRoot™ RCS

Root Canal Sealer

High seal, and much more



**ACTIVE
BIOSILICATE
TECHNOLOGY**

We know that failure of a root canal treatment can have severe consequences for you and your patients.

With BioRoot™ RCS, move to a new generation of mineral obturation offering you an innovative combination of features:

- High Seal
- Antimicrobial properties
- Promotes peri-apical healing
- Easy obturations and follow-up

BioRoot™ RCS. Succeed.

